

AMENDMENTS TO THE SPECIFICATION

Please amend paragraph [0034] as follows:

[0034] (3) Durability (Resistance to crack growth by bending)

The test of crack growth by bending is carried out according to JIS K6260 to measure the bending number until the crack length becomes 12 cm, which is shown by an index on the basis that Comparative Example 6 is 100. The ~~[[lager]]~~ larger the index value, the larger the bending number and the better the resistance to crack growth by bending and the better the durability.